

CHEMICAL PROPERTIES ASSOCIATED WITH BACTERIAL WETWOOD IN RED OAKS

Zicai Xu

Graduate Research Assistant
Department of Forest Resources
Clemson University
Clemson, SC 29634-0331

Theodor D. Leininger

Principal Research Plant Pathologist
Southern Hardwoods Laboratory
USDA Forest Service
Stoneville, MS 38776

and

Andy W. C. Lee and Frank H. Tainter

Professors
Department of Forest Resources
Clemson University
Clemson, SC 29634-0331

(Received March 2000)

ABSTRACT

Bacterial wetwood is a major cause of value loss in the red oak lumber industry in the United States. Red oak trees in Mississippi, South Carolina, and Florida were sampled and evaluated for certain chemical properties possibly associated with the wetwood condition. Specific variables investigated were pH and concentrations of methane, cations (Na^+ , Ca^{++} , K^+ , and Mg^{++}), nonstructural carbohydrates, and organic acids (acetate, propionate, and butyrate).

The degree of bacterial wetwood infection and development was greater in red oaks from Mississippi than from South Carolina as evidenced by increased concentrations of methane, total Na^+ , total K^+ , total Ca^{++} , and by decreased concentrations of total sugar and reducing sugar. Of all the variables tested, methane concentration was the best indicator of wetwood in living red oak trees at all three locations. pH was not an indicator of wetwood in living trees or in green red oak lumber. Of the remaining variables tested, greater concentrations of acetic acid, total K^+ , and lesser concentrations of nonstructural carbohydrates characterized wetwood-affected trees, but their potential as wetwood indicators depends on wetwood severity, not its mere presence.

Keywords: Chemical properties, wetwood, red oaks, tree disease identification.

INTRODUCTION

Red oaks are very important commercial trees in the United States. In 1991, more than 3.5 MBF, 36% of the total lumber in the U.S. hardwood market, was comprised of red oak (Murdoch 1992). The widespread occurrence of bacterially infected wetwood is an ongoing concern in the production and continued uti-

lization of quality red oak lumber. Since wetwood-affected oak is more prone to develop honeycomb, ring failure, and surface checking than is healthy oak (McMillen et al. 1979; Ward 1972), the hardwood industry suffers a great financial loss due to the reduction in quality of red oak lumber. This fact was brought to the attention of the Hardwood Research Council in 1983 (Murdoch 1992).

Since that time, concerns also have been raised about the identification of living wetwood-affected oak trees in the forest. Mild-drying schedules can be applied to wetwood-affected lumber to reduce drying defects if it is identified and separated from healthy lumber before drying. However, it is difficult to recognize the presence of wetwood in red oak boards on the green chain during the milling operation. At present, the only practical way to identify wetwood is to sniff the fresh heartwood to detect the characteristic sour odors of fatty acids, and other compounds produced by the bacterial populations associated with the disease. This technique is fallible and may lead to identification errors because the human nose rapidly suffers "overload" (Murdoch 1992).

There are still no consistently reliable methods of detecting the presence of wetwood in red oaks. An accurate wetwood detection system would greatly benefit the hardwood lumber industry. Chemical properties appear to be good potential indicators of wetwood since wetwood is always associated with changes in wood chemical properties. For example, wetwood pH usually differs from the pH of adjacent normal wood; it tends to be more acidic in conifers (Bauch et al. 1975; Hartley et al. 1961), and more alkaline in hardwoods (Carter 1945; Hartley et al. 1961). Moisture content is usually greater in wetwood-affected wood (Toole 1968) because the absorptive and moisture-holding capacity of wetwood is increased by bacterial slime and heavy deposition of extractives (Ward and Zeikus 1980). Concentrations of cations such as Ca^{++} , K^+ , and Na^+ are often elevated in some tree species (Murdoch et al. 1987). Calcium carbonate crystals were detected in the wetwood of Japanese poplar (*Populus maximowiczii* Henry) (Fukazawa et al. 1985). The fermentative action of wetwood bacteria produces gas with pressures recorded up to 4.22 Kg/cm² (60 lb per square inch) (Hamilton 1980). These high pressures often force accumulated gas and sap from the trunk through cracks in branch crotches, wounds made by removing branches, or through other

injuries. The flux is colorless to tan at first, but darkens upon exposure to the air, leaving a light gray encrustation on the bark (Stipes 1971). Bacterial-affected heartwood in oak is associated with unpleasant, sour, or rancid odors that are not characteristic of normal, uninfected heartwood. The fatty acids responsible for these odors are produced by anaerobic bacteria (Ward 1982; Ward and Zeikus 1980). The acid mixture consists of acetate with a strong vinegar odor, butyrate with an odor similar to rancid butter, valerate with a putrid odor, and caproate with a goat odor. Anaerobic bacteria isolated from bacterial oak will produce sour and rancid odors in laboratory cultures similar to the abnormal odors found in the oak wetwood (Ward 1982).

This investigation compared pH and concentrations of methane, Na^+ , Ca^{++} , K^+ , Mg^{++} , nonstructural carbohydrates, and organic acids measured in wetwood to these variables measured in healthy wood of red oaks to determine their potential for use as possible predictors of wetwood.

MATERIALS AND METHODS

Sites and sample trees

Chemical variables were measured for sixty-two red oak trees in the Clemson Experimental Forest in Pickens County, South Carolina (SC), ten red oaks in the Delta National Forest in Sharkey Co., Mississippi (MS), and twenty red oaks on Anderson-Tully Co. land in Issaquena Co., MS. Fourteen oak trees were sampled in Leon, Hillsborough, and Sarasota counties, Florida (FL), but only for methane content. The number of trees associated with the measurement of each chemical variable is listed in Tables 1–5. The sample sites and tree species selected in SC and MS are described in detail in Xu et al. (2000). The tree species selected in FL were: water oak (*Quercus nigra* L.) (No. = 5), live oak (*Q. virginiana* Mill.) (No. = 3), laurel oak (*Q. hemisphaerica* Bartr.) (No. = 4), and swamp laurel oak (*Q. laurifolia* Michx.) (No. = 2). The sample trees were located in low and wet sites.

TABLE 1. Average methane concentrations as related to wetwood health status of red oak trees in South Carolina, Mississippi, and Florida.

Health status	South Carolina		Mississippi		Florida	
	n	Methane concentration (ppm)	n	Methane concentration (ppm)	n	Methane concentration (ppm)
WW ²	25	432.9 a ¹ , B ¹	17	735.5 a, A	6	577.1 a, B
NW	21	72.4 b, A	9	24.2 b, A	8	45.8 b, A

¹ Means with the same uppercase letter within each row, or with the same lowercase letter within each column, are not significantly different at $P = 0.05$.

² WW = wetwood; NW = normal wood.

Sampling and statistical method

All trees were arbitrarily selected regardless of age, DBH, height, and other physical properties. Trees in SC were selected in February 1997, sampled for pH in July, sampled for methane in September, and sampled for other chemical parameters in July 1998. Sampling of trees in MS for pH and methane was in September 1997, and for other chemical parameters in July 1998. Sampling of trees in FL occurred in September 1997. Based on the odor of an increment core removed from the bole at 1.4 m above the ground, the sample trees were initially classified as wetwood infected (WW) or normal (NW). This technique is recognized as standard for identifying bacterial wetwood in the field (Murdoch 1992) and has been used in other studies (Verkasalo et al. 1993; Ross et al. 1992, 1994). In addition to the foul odor, bacterial wetwood may have a dark, water-soaked appearance that distinguishes it from healthy wood. Sample trees were cut down in order to obtain boards and wood tissue for this and a related study (Xu et al. 2000). While bacterial infections were not verified by culturing or visual inspection with a microscope, only the most obviously infected trees were selected for study based on odor and appearance. Wetwood normally occurs in a cone-shaped region in the heartwood of infected trees, which makes it fairly easy to detect once a tree is down. Based on the odor of increment cores, it appeared that the degree of wetwood infection in MS trees was greater than that of SC wetwood trees. Analysis of variance and Duncan's Multiple Comparison Test ($P = 0.05$) were used to analyze the data

to determine differences between WW and NW for pH and concentrations of methane, nonstructural carbohydrates, organic acids, and some nutrient minerals.

Methane concentrations

Increment cores (12 cm long) were placed into screw-cap tubes (10 × 125 mm) immediately after being removed from the sample trees. Each tube was sealed with a rubber septum and an open-top closure, and placed on ice for transport to the lab. In the laboratory, samples were stored in a freezer at -5°C until they were analyzed. Samples were warmed to room temperature prior to analyzing them for methane concentrations using a gas chromatograph (Varian 3400) with a flame ionization detector and a packed column (3.3 mm Porapak 70–100 mesh). The injection amount was 1 ml, and the carrier gas was N_2 with a flow rate of 25 ml/min. Gas chromatograph temperatures were as follows: injector 150°C ; column 50°C ; and detector 250°C . Methane concentrations were calculated based on the areas beneath response peaks. The standard was 103 ppm methane in helium (National Specialty Gases, Research Triangle Park, NC). The final methane concentrations were calculated based on the areas of the methane peaks in samples compared to the areas of the methane peaks in standards.

Total cation concentrations (Na^+ , K^+ , Ca^{++} , and Mg^{++})

Wood samples, ground into flour able to pass a 0.5-mm sieve, were oven-dried at 103°C to a constant weight. Approximately 2

g of dried wood flour was reduced to ash in a muffle furnace (Model E555C-1, BLUE M Electric Co., Blue Island, IL) at 550°C for 4 hours. The ash was dissolved in 10 ml 6 N HCl and diluted into 1:10 and 1:100 solutions with 6 N HCl. These solutions were injected into an Atomic Absorption Spectrophotometer (Model 5000, Perkin-Elmer Co., Norwalk, CT) in order to measure total Na⁺, K⁺, Ca⁺⁺, and Mg⁺⁺.

Nonstructural carbohydrates

Nonstructural carbohydrates (sugars and glucose) were extracted from wood samples ground to pass through a 0.5-mm sieve, and then dried in an oven. The extraction was done using 80% ethanol heated in a Soxhlet extraction apparatus for 6 hours. The resulting extraction solution was then assayed for total sugars using the phenol-sulfuric acid method (Dubois et al. 1956) and reducing sugars by Nelson's test (Clark 1964). The wood flour remaining after the extraction was then measured for starch content using a starch assay kit (SA-20, SIGMA). Sugar and reducing sugar concentrations for each sample were determined by averaging the results from three different dilutions of the same sample.

Organic acid concentrations

Wetwood sap was collected from fresh bolts cut from sample red oak trees at 1.4 m above the ground. Fluid was expressed using a hydraulic press capable of pressures up to 15 Mpa, and then centrifuged (DYNAC II centrifuge, Becton Dickinson, Sparks, MD) for 5.0 min at 10,000 rpm. Aliquots of 100 µL were injected into a high performance liquid chromatograph equipped with a Waters 490 Programmable Multiwavelength Detector and a Waters Spherisorb® 3µm ODS2 4.6 × 150 mm analytical column (Waters Corporation, Milford, MA). The mobile phase at 20°C was 0.1 N methanesulfonic acid (0.025M n-octylamine was added into 2 L 0.1 N methanesulfonic acid) at a flow rate of 1.5 ml/min. The geometric areas under sample response peaks

were used to quantify organic acid concentrations. A measurement standard consisted of 1 ml each of propionate and butyrate, and 0.5 ml of acetate, brought to 100 ml with the mobile phase.

pH

pH was measured in sap samples. To obtain sap, a fresh increment core was put into a polyethylene tube, and the tube containing the core was compressed with a hydraulic press. The pH of the expressed sap was measured with a pH meter (Accumet Model 910, Fisher Scientific Co., Pittsburgh, PA.).

RESULTS

Methane concentrations

Methane concentrations were significantly greater in wetwood trees than in healthy trees in SC, MS, and FL (Table 1). The average methane concentration in MS wetwood trees (735.5 ppm) was significantly greater than that in SC (432.9 ppm) and FL (577.1 ppm) wetwood trees.

Total cation concentrations

The MS wetwood trees had significantly greater concentrations of total Na⁺, K⁺, Ca⁺⁺, and Mg⁺⁺ than did SC trees (Table 2). Concentrations of Na⁺ and K⁺ were also greater in the healthy wood of MS trees compared to that of SC trees. In MS trees, total Na⁺, K⁺ and Mg⁺⁺ concentrations were significantly greater in wetwood trees (Na⁺: 25.7 ppm; K⁺: 1133.8 ppm and Mg⁺⁺: 230.0 ppm) than in healthy trees (Na⁺: 14.2 ppm; K⁺: 368.8 ppm and Mg⁺⁺: 115.4 ppm). In SC trees, total K⁺ and Ca⁺⁺ concentrations were significantly greater in wetwood trees (K⁺: 366.7 ppm and Ca⁺⁺: 700.5 ppm) than in healthy trees (K⁺: 243.2 ppm and Ca⁺⁺: 485.7 ppm).

Nonstructural carbohydrate concentrations

Total sugar and reducing sugar concentrations were significantly less in wetwood and healthy trees in MS compared to wetwood and

TABLE 4. *Organic acid concentrations in the sap of South Carolina and Mississippi red oak trees as related to wetwood health status.*

Health status	n		Acetate (mM)		Propionate (mM)		Butyrate (mM)	
	Mississippi	South Carolina	Mississippi	South Carolina	Mississippi	South Carolina	Mississippi	South Carolina
WW ²	5	18	66.1 a ¹ , A ¹	34.0 a, B	0.0 a, B	4.0 a, A	9.7 a, A	16.1 a, A
NW	4	14	30.3 b, A	13.5 b, B	0.0 a, B	1.9 a, A	5.0 a, A	5.8 b, A

¹ Means with the same uppercase letter within each pair (SC versus MS) in each row, or with the same lowercase letter within each column, are not significantly different at *P* = 0.05.

² WW = wetwood; NW = normal wood.

located on poorly drained soils, particularly in low-lying areas surrounding lakes and rivers (Zeikus and Ward 1974). The results of the present study suggest that methane is common in red oak trees, and that while the mere presence of methane might not indicate wetwood, a concentration that is six to thirty times greater than that of healthy trees indicates the presence of wetwood. Methane is relatively easy and quick to measure with a gas chromatograph. However, a disadvantage of using methane as an indicator of wetwood in lumber is that methane quickly volatilizes after the tree is cut.

Mineral elements are essential for tree growth. The essential elements supplied from soil include P, K, Ca, Mg, Cu, Zn, B, Fe, Mn, and Mo (Hocker 1979). These mineral elements are taken up by tree roots and accumulate in the tree. The elements may also return to the soil through secretions, by leaching from roots, and by annual litter fall (e.g., leaves, twigs, flowers, and fruits). Each living tree contains certain relative amounts of these essential elements. Our results show that Na⁺, K⁺, Ca⁺⁺ and Mg⁺⁺ concentrations increased in wetwood-affected MS and SC trees, al-

though not all were significant differences. This phenomenon has been reported for wetwood in many tree species (including those in which higher concentrations of mineral nutrients were found in wetwood-infected heartwood, and in young trees (Fukazawa et al. 1985; Worrall and Parmeter 1982). Murdoch et al. (1987) suggested that the elevated levels of cations in wetwood resulted from the selective degradation of cell membranes by wetwood bacteria, leading to leakage of woody cell contents. Over time, this would lead to the accumulation of cations. It is believed that this concentration of cations accounts for an increase in osmotic potential in wetwood, which leads to the accumulation of water in wetwood-affected heartwood tissues (McLemore et al. 1999; Worrall and Parmeter 1982). Of the four cations measured in the present study, K⁺ concentrations were the most different between healthy and wetwood trees in MS, which suggests that K⁺ concentration could serve as an indicator of wetwood in MS red oaks. Concentration of Ca⁺⁺ may serve as a good indicator of wetwood in SC oaks. In general, cation concentrations could be good indicators of the severity of wetwood since the accumulation of cations seems to correlate with the formation of wetwood, especially in severely affected wood. An advantage of using cation concentrations as indicators of wetwood is that a minimal amount of sample is needed, and living trees could be nondestructively sampled by using increment cores.

Very little has been published regarding wetwood and nonstructural carbohydrates. Nonstructural carbohydrates are found in all

TABLE 5. *Average pH as related to wetwood health status of red oak trees in South Carolina and Mississippi.*

Health status	South Carolina		Mississippi	
	n	pH	n	pH
WW ²	25	3.8 a ¹ , A ¹	5	3.7 a, A
NW	16	3.7 a, A	5	3.6 a, A

¹ Means with the same uppercase letter within each row, or with the same lowercase letter within each column, are not significantly different at *P* = 0.05.

² WW = wetwood; NW = normal wood.

living plants. Plants store energy as starch, which is in a dynamic state since plants can convert starch to sugar and then change sugar back to starch. Therefore, starch concentrations vary with season and with a number of other environmental factors. Sugars and starch occur in the cytoplasm and can be easily accessed and metabolized by bacteria. Significant differences were detected in total sugar and reducing sugar concentrations in SC and MS trees with wetwood when compared to healthy trees. The lower concentrations of nonstructural carbohydrates in MS trees compared to those of SC trees suggest that MS wetwood trees had more severe infections compared to SC wetwood trees. Even if this study had detected differences in starch concentrations between wetwood and healthy wood, it is unlikely that starch concentrations would be a good predictor of wetwood since even healthy heartwood contains little starch. Total sugars and reducing sugars could confirm the presence of severe wetwood, but since this measurement is destructive and time-consuming, it probably is not a good predictor of wetwood in red oaks.

According to McMillen et al. (1979), the presence of rancid odors (from butyrate and valerate) indicates advanced or severe bacterial infections. A strong vinegar odor (from acetate) usually indicates early, and less severe, bacterial infection. The results of the present study do not agree with their research since we measured more acetate and less butyrate in MS and SC wetwood trees overall, and the severely infected trees in MS had less butyrate and more acetate than did the moderately wetwood-affected trees in SC. Acetate concentrations increased significantly in response to wetwood infection in both SC and MS trees, but only in SC trees was increased butyrate related to wetwood infection. Acetate concentration has the potential to be a good indicator of wetwood since it can, to a certain degree, reflect wetwood severity. The measurement of organic acids, collected from the sap of fresh increment cores could be a useful

nondestructive approach to detect wetwood in living trees.

Previous studies that compared the pH of healthy and wetwood-affected heartwood were not in agreement. Schroeder and Kozlik (1972) found that the pH values of wetwood and normal heartwood in western hemlock were identical. Toole (1968) found that wetwood in cottonwood had a higher pH compared to normal sapwood. Wetwood of other species can be either more alkaline or more acidic than healthy wood (Ward and Pong 1980). The present research found no differences in pH between healthy and wetwood trees, which suggests that pH is not a good indicator of wetwood in oaks.

CONCLUSIONS

This study suggests that the degree of bacterial wetwood infection and development as measured by a number of chemical variables is greater in MS trees than in SC trees. These results support the results of a related study using these same trees which defined some mechanical and drying properties of bacterially infected and healthy woods (Xu et al. 2000). Among all the chemical variables tested, the relative methane concentrations appear to be the best indicator of wetwood in red oak. Greater concentrations of total K^+ , Ca^{++} , Mg^{++} and acetate, and concentrations of total and reducing sugars were also characteristic of certain wetwood-affected red oaks. However, these variables are less useful than methane concentrations, to indicate the presence of wetwood infections, because they were not associated with all wetwood infections.

REFERENCES

- BAUCH, J., W. HÖLL, AND R. ENDEWARD. 1975. Some aspects of wetwood formation in fir. *Holzforschung* 29: 198-205.
- CARTER, J. C. 1945. Wetwood of elms. *Illinois Nat. Hist. Surv. Bull.* 23:407-488.
- CLARK, JOHN M., JR., ed. 1964. *Experimental biochemistry*. W. H. Freeman and Company, San Francisco, CA. 228 pp.
- DUBOIS, M., K. A. GILLES, J. K. HAMILTON, P. A. REBERS, AND F. SMITH. 1956. Colorimetric method for determi-

- nation of sugars and related substances. *Anal. Chem.* 28:350-356.
- FUKAZAWA, K., M. UJIE, L. KI-YEONG, AND T. ISHII. 1985. Inorganic constituents in wood relation to wetwood and crystal formation. Symposium on Forest Products Research International—Achievements and the Future, 22-26 April 1985, CSIR Conference Centre, Pretoria, Republic of South Africa 16.15.1-16.15.9.
- HAMILTON, W. D. 1980. Wetwood and slime flux in landscape trees. *J. Arbor.* 6:247-249.
- HARTLEY, C., R. W. DAVIDSON, AND B. S. CRANDALL. 1961. Wetwood, bacteria, and increased pH in trees. *USDA For. Prod. Lab. Rep. No. 2215*. Madison, WI. 34 pp.
- HOCKER, JR., H. W. 1979. *Introduction to forest biology*. John Wiley & Sons Inc., New York, NY. 467 pp.
- MCLEMORE, J. B., W. C. BRIDGES, A. W. LEE, AND F. H. TAINTER. 1999. Selected mechanical and physical properties of Chilean tepe wood affected by butterfly stain. *Forest Prod. J.* 49(2):59-64.
- McMILLEN, J. M., J. C. WARD, AND J. CHERN. 1979. Drying procedures for bacterially infected northern red oak lumber. *USDA For. Prod. Lab. Res. Pap. FPL 345*. Madison, WI. 15 pp.
- MURDOCH, C. W. 1992. Detection system to identify wetwood in standing living trees and in cut logs and boards. *Transferring Technology for Industry No. 1* ISSN 1064-3452. Beltsville, MD. 15 pp.
- , R. J. CAMPANA, AND C. J. BIERMANN. 1987. Physical and chemical properties of wetwood in American elm (*Ulmus americana*). *Can. J. Pl. Path.* 9:20-23.
- PRESCOTT, L. M., J. P. HARLEY, AND D. A. KLEIN. 1990. *Microbiology*. 2nd ed. Wm. C. Brown Publishers. Dubuque, IO. 912 pp.
- ROSS, R. J.; J. C. WARD, AND A. TENWOLDE. 1992. Identifying bacterially infected oak by stress wave nondestructive evaluation. *USDA For. Prod. Lab. Res. Pap. FPL 512*. Madison, WI. 6 pp.
- , ———, AND ———. 1994. Stress wave nondestructive evaluation of wetwood. *Forest Prod. J.* 44(7/8):79-83.
- SCHROEDER, H. A., AND C. J. KOZLIK. 1972. The characterization of wetwood in western hemlock. *Wood Sci. Technol.* 6:85-94.
- STIPES, R. J. 1971. Wetwood of landscape trees in Virginia. *Plant Disease Control Notes, Extension Division, Virginia Polytechnic Institute, Blacksburg, VA. Control Series 139*. 2 pp.
- TOOLE, E. R. 1968. Wetwood in cottonwood. *Plant Disease Rep.* 52:822-823.
- VERKASALO, E., R. J. ROSS, A. TENWOLDE, AND R. L. YOUNGS. 1993. Properties related to drying defects in red oak wetwood. *USDA For. Prod. Lab. Res. Pap. FPL 516*. Madison, WI. 10 pp.
- WARD, J. C. 1972. Anaerobic bacteria associated with honeycomb and ring failure in red and black oak lumber. *Phytopathology* 62:796.
- . 1982. Bacterial oak and how to dry it. *Southern Lumberman* 243:8-11.
- , AND W. Y. PONG. 1980. Wetwood in trees: A timber resource problem. *USDA For. Serv., Gen. Tech. Rep. PNW-112*. 56 pp.
- , AND J. G. ZEIKUS. 1980. Bacteriological, chemical and physical properties of wetwood in living trees. Pages 113-166 in J. Bauch, ed. *Natural variations of wood properties. Mitteilungen der Bundesforschungsanstalt für Forst-und Holzwirtschaft Nr.131*. Hamburg-Reinbek: Max Wiedehusen Verlag.
- WORRALL, J. J., AND J. R. PARMETER, JR. 1982. Formation and properties of wetwood in white fir. *Phytopathology* 72:1209-1212.
- XU, Z., T. D. LEININGER, A. W. C. LEE, AND F. H. TAINTER. 2000. Physical mechanical, and drying properties associated with bacterial wetwood in red oaks. *Forest Prod. J.* (submitted).
- ZEIKUS, J. G., AND J. C. WARD. 1974. Methane formation in living trees: A microbial origin. *Science* 184:1181-1183.